

# Flexible tile adhesive











Material number	Contents	Unit of quantity	Packaging	Colour
201000001	25	KG	Bag	Cement grey

## **Product features**

- Cementitious tile adhesive
- C2 TE in accordance with DIN EN 12004
- Can be walked on and joined after ca. 24 hours
- Long working time of approx. 2 hours

# **Advantages**

- Tested system product
- Economical application

# **Areas of application**

- For laying ceramic tiles and boards using thin-bed laying
- for heated and unheated substrates
- For walls and floors
- For interior and exterior use





## **Existing test certificates**

- Conformity DIN EN 12004
- Reaction to fire classification report
- EMICODE licence

## **Technical Data**

## Material properties

Base material	sand cement Additive
Density (spec. weight)	approx. 1.35 g/cm <sup>3</sup>
Classification of the reaction to fire in accordance with DIN EN 13501-1	Al
Mixing	
Maturing time	approx. 3 minutes
Water addition	from 7   to 8.25
Application	
Consumption pro m <sup>2</sup> and mm layer thickness	approx. 1 kg/m²
Foot traffic after	approx. 24 hours
Consumption with 6mm notched trowel	2.1 kg/m²
Consumption with 8mm notched trowel	2.8 kg/m²
Consumption with 10mm notched trowel	3.5 kg/m²
Application temperature	from 5 °C to 25 °C
Hardening time / full resilience	approx. 7 days
Open time	approx. 30 minutes
Adhesive open time (min.)	≥ 20 minutes

# **Application technology**

# Aids/tools

- Toothed trowel
- Stirrer
- Trowel
- Occupational safety equipment

# Suitable substrate

- Concrete, cement screed (CT), floor levelling compounds, calcium sulphate screeds (CA, CAF), mastic asphalt screeds (AS), magnesia screeds (MA)
- Tile bearing elements, gypsum fibre boards, gypsum boards, raised floors, cement and fibre cement boards, decoupling mats & panels, dry screeds
- Cement-based plaster, gypsum plaster, cement-lime plaster, lightweight plaster
- Bonded waterproofing; the suitability of the substrate must be checked and observed, taking into account the planned water impact class of DIN 18534 and DIN 18531.
- Firmly adhering tiled finishes

## **Substrate preparation**

## Requirement for substrate

- 1. Load-bearing
- **2**. Dry
- 3. Even
- 4. Sealed in the surface
- 5. Free of cracks
- 6. Free of adhesion inhibiting substances and laitance layers





### Measures for substrate preparation

The requirements in DIN 18157 - 1 and the recognised technical standards are essential for preparing the application substrates.

#### Preparing the surface

- 1. Check the application substrate and determine the moisture content using the CM method.
- 2. Remove impurities, adhesion-reducing substances and binder accumulations/laitance layers.
- 3. Prime absorbent substrates with ASO-Unigrund-GE or ASO-Unigrund-K.
- 4. Prime non-absorbent substrates with ASO-Unigrund-S.

#### Moisture content of the CM measurement

	max. CM moisture readings
CT for screeds on insulation or a separating layer	≤ 2.0 CM %
CA without floor heating system	≤ 0.5 CM %
CA <b>with</b> floor heating system	≤ 0.3 CM %

## Usage

#### Mixing

- 1. Put the water into a clean mixing bucket and mix with the powder component with a stirrer to produce a homogeneous, lump-free mass.
- 2. After a settling period of ca. 3 minutes, thoroughly homogenise the compound again.
- 3. Do not mix more material than can be applied during the pot life.

#### Application

- 1. Spread the mixed mortar evenly across the substrate surface and comb through with a suitable notched trowel to suit the board size.
- 2. Apply the surfacing materials within the adhesive open time.

## Cleaning tools

Rinse tools with water immediately after use.

#### Storage conditions

#### Storage

Store in a cool and dry place. Min. 12 months in the original canister. Promptly use opened canister.

## Disposal

Product leftovers can be disposed of in accordance with disposal code AVV 17 01 01.

#### **Emission behaviour / building certification systems**

- Very low emissions in accordance with GEV-EMICODE, which normally results in positive evaluations within the scope of building certification systems in accordance with DGNB, LEED, BREEAM, HQE.
- Maximum quality level 4, line 8 in accordance with DGNB criteria "ENV 1.2 Risks to the local environment".

## Notes

- When laying natural stone and synthetic stone, the product-specific properties of the coating materials (tendency to discolour, risk of curling, etc.) and the laying recommendations of the manufacturer must be taken into account. We recommend carrying out trial laying!
- Rooms, surfaces and building components that expect water exposure in accordance with DIN 18534, DIN 18531 and DIN 18535 must be protected by bonded waterproofing.
- Calcium sulphate screeds must be protected with the ASO<sup>®</sup>-Unigrund-GE or ASO<sup>®</sup>-Unigrund-K primer prior to laying. Calcium sulphate screeds must be protected with a barrier primer (e.g. ASODUR<sup>®</sup>-GBM) when laying large format tiles.
- Do not stir or add water to existing material that has already set in order to make it workable again.
- Use a barrier primer such as ASODUR<sup>®</sup>-GBM to protect substrates that are sensitive to moisture, such as magnesite screeds, from direct contact.
- Protect the product from water, frost, draughts, direct sunlight and mechanical loads until it has dried completely.






Planning, inspection of substrates and building site circumstances, laying, grouting and subsequent care of the work must be done in accordance with the relevant DIN standards and recognised rules of technology (e.g. the ZDB sheets of the Zentralverband Deutsches Baugewerbe e.V.) in the latest version.

GISCODE: ZP1

#### **Annotations**

Conformity / Declaration / Verification



The rights of the buyer with regard to the quality of our materials are based on our terms and conditions of sale and delivery. Our technical advice team will be happy to advise you in the case of requirements that exceed the scope of the application described here. In order to be binding, a legally binding written confirmation is required. The product description does not release the user from a duty of care. Lay a test area in the event of uncertainty. This version becomes invalid in the event of a new version being issued.

SCHOMBURG GmbH & Co. KG · Aquafinstr. 2-8 · D-32760 Detmold (Germany) · Tel. +49-5231-953-00 · Fax +49-5231-953-333 · schomburg.com

