

Page 1/8

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 27.09.2023

Version number 1

Revision: 27.09.2023

SECTION 1: Identification of the substance/mixture and of the company/undertaking

1.1 Product identifier

· Trade name: MONOFLEX-S2

- 1.2 Relevant identified uses of the substance or mixture and uses advised against
- Sector of Use SU19 Building and construction work
- · Application of the substance / the mixture Tile adhesive
- 1.3 Details of the supplier of the safety data sheet
- **Manufacturer/Supplier:** SCHOMBURG GmbH & Co. KG Aquafinstr. 2-8 D-32760 Detmold Germany

Tel: ++49 (0)5231/953-00 Fax: ++49 (0)5231/953-123 email: info@schomburg.de web: www.schomburg.de

• Informing department: Department: Environment and Safety

If you have any questions about the Environment and Safety Department, please contact our department.

e-Mail: SDB@schomburg.de

SECTION 2: Hazards identification

2.1 Classification of the substance or mixture
 Classification according to Regulation (EC) No 1272/2008

corrosion

Eye Dam. 1 H318 Causes serious eye damage.



Skin Irrit. 2 H315 Causes skin irritation. Skin Sens. 1 H317 May cause an allergic skin reaction.

2.2 Label elements

- · Labelling according to Regulation (EC) No 1272/2008
- The product is classified and labelled according to the GB CLP regulation.
- Hazard pictograms GHS05, GHS07
- · Signal word Danger
- Hazard-determining components of labelling: calcium sulfoaluminate cement
- · Hazard statements
- H315 Causes skin irritation.
- H318 Causes serious eye damage.

Printing date 27.09.2023

Version number 1

Revision: 27.09.2023

Trade name: MONOFLEX-S2

	(Contd. of page 1)
H317 May caus	e an allergic skin reaction.
· Precautionary	statements
P261	Avoid breathing dust/fume/gas/mist/vapours/spray.
P264	Wash thoroughly after handling.
P280	Wear protective gloves / eye protection / face protection.
P305+P351+P3	338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact
	lenses, if present and easy to do. Continue rinsing.
P333+P313	If skin irritation or rash occurs: Get medical advice/attention.
P501	Dispose of contents/container in accordance with local/regional/national/
	international regulations.
· 2.3 Other haza	rds

· Results of PBT and vPvB assessment

· **PBT:** Not applicable.

• **vPvB:** Not applicable.

SECTION 3: Composition/information on ingredients

- · 3.2 Mixtures
- · Description: Product based on cement and mineral filler.
- Dangerous components:

EC number: 934-133-9 calcium sulfoaluminate cement

calcium sulfoaluminate cement
 Eye Dam. 1, H318;
 Skin Irrit. 2, H315; Skin Sens. 1, H317;
 STOT SE 3, H335

10-25%

• Additional information For the wording of the listed hazard phrases refer to section 16.

SECTION 4: First aid measures

- 4.1 Description of first aid measures
- · General information

Symptoms of poisoning may even occur after several hours; therefore medical observation for at least 48 hours after the accident.

Personal protection for the First Aider.

It is possible to choke in case of vomiting in unconsciousness.

Bring unconscious persons into a stable position on side.

Keep the respiratory tract free (remove dentures and vomiting).

Check the pulse. In case of heart failure you have to make a cardiac massage. In case of stoppage of breathing: artificial respiration.

- Take up a doctor immediately!
- After inhalation

Supply fresh air or oxygen; call for doctor.

In case of unconsciousness bring patient into stable side position for transport.

Supply fresh air and call for doctor for safety reasons.

After skin contact

Instantly wash with water and soap and rinse thoroughly.

Wash with water and soap.

After contact, clean the skin mechanical and rinse with water and soap.

Change immediately contaminated clothes.

• After eye contact Rinse opened eye for several minutes under running water. Then consult doctor.

- · After swallowing
- Do not induce vomiting; instantly call for medical help.

Drink copious amounts of water and provide fresh air. Instantly call for doctor. Show the packaging or the label to the doctor.

- 4.2 Most important symptoms and effects, both acute and delayed
- No further relevant information available.

(Contd. on page 3)

GB

Printing date 27.09.2023

Version number 1

Revision: 27.09.2023

Trade name: MONOFLEX-S2

• 4.3 Indication of any immediate medical attention and special treatment needed No further relevant information available.

(Contd. of page 2)

SECTION 5: Firefighting measures

- · 5.1 Extinguishing media
- Suitable extinguishing agents

CO2, extinguishing powder or water jet. Fight larger fires with water jet.

- 5.2 Special hazards arising from the substance or mixture
- Formation of poisonous gases during heating or in fires.
- 5.3 Advice for firefighters
- · Protective equipment: Wear self-contained breathing apparatus.
- · Additional information

Dispose of fire debris and contaminated fire fighting water in accordance with official regulations. Follow the emergency-plan.

SECTION 6: Accidental release measures

• 6.1 Personal precautions, protective equipment and emergency procedures Bring persons out of danger.

- Wear protective equipment. Keep unprotected persons away.
 6.2 Environmental precautions:
 Do not allow product to reach sewage system or water bodies.
 Inform respective authorities in case product reaches water or sewage system.
 The product may not leak out in sewerage system, stretch of water or soil.
- 6.3 Methods and material for containment and cleaning up: Ensure adequate ventilation.
- Pick up the product mechanically, avoid dust formation.
- 6.4 Reference to other sections
 See Section 7 for information on safe handling
 See Section 8 for information on personal protection equipment.
 See Section 13 for information on disposal.

SECTION 7: Handling and storage

7.1 Precautions for safe handling Ensure good ventilation/exhaustion at the workplace. Prevent formation of dust. Keep away from children.

- · Information about protection against explosions and fires: No special measures required.
- 7.2 Conditions for safe storage, including any incompatibilities
- · Storage
- Requirements to be met by storerooms and containers: No special requirements.
- · Information about storage in one common storage facility:
- Please follow the rules of the VCI-Storage-Concept for chemicals.
- · Further information about storage conditions: None.
- 7.3 Specific end use(s) No further relevant information available.

SECTION 8: Exposure controls/personal protection

- · 8.1 Control parameters
- Components with critical values that require monitoring at the workplace:

1317-65-3 Calciumcarbonat (25-50%)

WEL Long-term value: 10* 4** mg/m³ *inhalable dust; **respirable

(Contd. on page 4)

GB

Printing date 27.09.2023

Version number 1

Revision: 27.09.2023

Trade name: MONOFLEX-S2

8.2 Exposure controls Appropriate engineering controls It must be possible to wash the skin in the working area. Eye-wash bottle must be available. Individual protection measures, such as personal protective equipment General protective and hygienic measures The usual precautionary measures should be adhered to in handling the chemicals. Instantly remove any solled and impregnated garments. Vacuum clean contaminated clothing. Do not blow or brush off contamination. Avoid contact with the eyes and skin. Do not eat, drink or smoke while working. Use skin protection cream for preventive skin protection. Be sure to clean skin thoroughly after work and before breaks. Breathing equipment: In case of brief exposure or low pollution use breathing filter apparatus. In case of intensive or long exposure use breathing apparatus that is independent of circulating air. Hand Protection: Do not reuse one-way-gloves Hand protection ream to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the glove aderial on consideration of the preparation times, rates of diffusion and the degradation Material of gloves <th>Additional information: The lists that were va</th> <th>(Contd. of page) Alid during the compilation were used as basis.</th>	Additional information: The lists that were va	(Contd. of page) Alid during the compilation were used as basis.
Appropriate engineering controls Imust be possible to wash the skin in the working area. Eye-wash bottle must be available. Individual protection measures, such as personal protective equipment General protective and hygienic measures The usual precautionary measures should be adhered to in handling the chemicals. Instantly remove any solied and impregnated garments. Vacuum clean contaminated clothing. Do not blow or brush off contamination. Avoid contact with the eyes and skin. Do not east, drink or smake while working. Use skin protection cream for preventive skin protection. Be sure to clean skin thoroughly after work and before breaks. Brathing equipment: In case of brief exposure or low pollution use breathing filter apparatus. In case of intensive or long exposure use breathing apparatus that is independent of circulating air. Hand Protection Do not reuse one-way-gloves Hand Protection In case of brief exposure or low pollution to the glove material can be given for the product/ the preparation. In case of brief exposure instruct. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation the chemical instruct. Selection of the gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitlable are e.g:		5
It must be possible to wash the skin in the working area. Eye-wash boutter must be available. Individual protection measures, such as personal protective equipment General protective and hygienic measures The usual precautionary measures should be adhered to in handling the chemicals. Instantly remove any solied and impregnated garments. Vacuum clean contaminated clothing. Do not blow or brush off contamination. Avoid contact with the eyes and skin. Do not eat, drink or smoke while working. Use skin protection cream for preventive skin protection. Be sure to clean skin throoughly after work and before breaks. Breathing equipment: In case of brief exposure or low pollution use breathing filter apparatus. In case of intensive or long exposure use breathing apparatus that is independent of circulating air. Hand protection: Nitrii-rubber-latex-gloves. In case of waring synthetic protective gloves use cotton-gloves as underwear. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. Due to missing tests no recommendation to the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g.: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Anseli : Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Shara / Gobi Nitex MPAP. Due-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanite 397 / Titansuperlite UYEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer of the protective gloves		
Eye-wash bottle must be available. Individual protection measures, such as personal protective equipment General protective and hygienic measures The usual precautionary measures should be adhered to in handling the chemicals. Instantly remove any solied and impregnated garments. Vacuum clean contaminated clothing. Do not blow or brush off contamination. Avoid contact with the eyes and skin. Do not eat, drink or smoke while working. Use skin protection cream for preventive skin protection. Be sure to clean skin thoroughly after work and before breaks. Breathing equipment: In case of brief exposure or low pollution use breathing filter apparatus. In case of intensive or long exposure use breathing apparatus that is independent of circulating air. Hand protection Do not reuse one-way-gloves In case of wearing synthetic protective gloves use cotton-gloves as underwear. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Ansel: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahar / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanitie 397 / Titansuperlite UVEX: user Profi Ergo XG 20 / user phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Section 9: Physical and chemical properties General Infor		king area.
Individual protection measures, such as personal protective equipment General protective and hygienic measures The usual precautionary measures should be adhered to in handling the chemicals. Instantly remove any solied and impregnated garments. Vacuum clean contaminated clothing. Do not blow or brush off contamination. Avoid contact with the eyes and skin. Do not eat, drink or smoke while working. Use skin protection cream for preventive skin protection. Be sure to clean skin thoroughly after work and before breaks. Breathing equipment: In case of brief exposure or low pollution use breathing filter apparatus. In case of intensive or long rexposure use breathing apparatus that is independent of circulating air. Hand protection Do not reuse one-way-gloves Hand Protection: Nitril-rubber-latex-gloves. In case of wearing synthetic protective gloves use cotton-gloves as underwear. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. Bue to missing tests no recommendation of the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Amperi: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Ansel: Flexiful 227 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo X28 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo X28 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo X28 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo X28 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo X28 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX		5
The usual precautionary measures should be adhered to in handling the chemicals. Instantly remove any solied and impregnated garments. Vacuum clean contaminated clothing. Do not blow or brush off contamination. Avoid contact with the eyes and skin. Do not est, dirink or smoke while working. Use skin protection cream for preventive skin protection. Be sure to clean skin throughly after work and before breaks. Breathing equipment: In case of brief exposure or low pollution use breathing filter apparatus. In case of intensive or long exposure use breathing apparatus that is independent of circulating air. Hand protection: Nitril-rubber-latex-gloves. In case of wearing synthetic protective gloves use cotton-gloves as underwear. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. Use to missing tests no recommendation of the genetration times, rates of diffusion and the degradation Material of gloves Sultable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Sultable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Ansel: Fiexifit L27 / Fieximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperite UVEX: uvex Prof Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Preparation time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Sec		rsonal protective equipment
Instantly remove any solied and impregnated garments. Vacuum clean contaminated clothing. Do not blow or brush off contamination. Avoid contact with the eyes and skin. Do not eat, drink or smoke while working. Use skin protection cream for preventive skin protection. Be sure to clean skin thoroughly after work and before breaks. Breathing equipment: In case of brief exposure or low pollution use breathing filter apparatus. In case of intensive or long exposure use breathing apparatus that is independent of circulating air. Hand protection Do not reuse one-way-gloves Hand Protection: Nitri-Inviber-latex-gloves. In case of wearing synthetic protective gloves use cotton-gloves as underwear. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. Bue to missing tests no recommendation of the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Ansell: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MPAP: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer of the protective gloves and has to be observed. SECTION 9: Physical and chemical properties Section 9: Physical and chemical properties General Information Physical State Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Seling point or initial boiling point and boiling rout or initial boiling point and	General protective and hygienic measures	
Vacuum clean contaminated clothing. Do not blow or brush off contamination. Avoid contact with the eyes and skin. Do not eat, drink or smoke while working. Use skin protection cream for preventive skin protection. Be sure to clean skin throughly after work and before breaks. Breathing equipment: In case of brief exposure or low pollution use breathing filter apparatus. In case of intensive or long exposure use breathing apparatus that is independent of circulating air. Hand protection Do not reuse one-way-gloves Hand Protection: Nitri-rubber-latex-gloves. In case of wearing synthetic protective gloves use cotton-gloves as underwear. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. Due to missing tests no recommendation of the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Anseli: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The xact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eyerface protection :Protective work clothing. SECTION 9: Physical and chemical properties G		
Avoid contact with the eyes and skin. Do not eat, drink or smoke while working. Use skin protection cream for preventive skin protection. Be sure to clean skin thoroughly after work and before breaks. Breathing equipment: In case of brief exposure or low pollution use breathing filter apparatus. In case of intensive or long exposure use breathing apparatus that is independent of circulating air. Hand protection: Not reuse one-way-gloves Hand Protection: NitriI-rubber-latex-gloves. In case of wearing synthetic protective gloves use cotton-gloves as underwear. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Anseli: Flexitrii L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperitie UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does ont only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Sylface protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information Physical state Solid mate		
Do not eat, drink or smoke while working. Use skin protection cream for preventive skin protection. Be sure to clean skin thoroughly after work and before breaks. Breathing equipment: In case of brief exposure or low pollution use breathing filter apparatus. In case of intensive or longer exposure use breathing apparatus that is independent of circulating air. Hand protection Do not reuse one-way-gloves Hand Protection: Nitril-rubber-latex-gloves. In case of wearing synthetic protective gloves use cotton-gloves as underwear. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/ the chemical mixture. Selection of the gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Anseli: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uwex Profi Ergo XG 20 / uwex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eyelface protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information Physical state Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting pointfreezing point: >1,000 °C Boiling point or initial boiling point and boiling		plow or brush off contamination.
Use skin protection cream for preventive skin protection. Be sure to clean skin thoroughly after work and before breaks. Breathing equipment: In case of brief exposure or low pollution use breathing filter apparatus. In case of intensive or longe exposure use breathing apparatus that is independent of circulating air. Hand protection Do not reuse one-way-gloves Hand Protection: NitriI-rubber-latex-gloves. In case of wearing synthetic protective gloves use cotton-gloves as underwear. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the dagradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g. Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Ansell: Flexitrii L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Sectrion 9 : Physical and chemical properties General Information Physical state Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: >1,000 °C Boiling point or initial boiling point and		
Be sure to clean skin thoroughly after work and before breaks. Breathing equipment: In case of brief exposure or low pollution use breathing filter apparatus. In case of intensive or long exposure use breathing apparatus that is independent of circulating air. Hand protection Do not reuse one-way-gloves Hand Protection: Nitril-rubber-latex-gloves. In case of wearing synthetic protective gloves use cotton-gloves as underwear. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. Due to missing tests no recommendation of the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (CISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Ansell: Flexitril L27 / Fleximax 27 or 35 / Hyite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several ubstances, the resistance of the glove material an not be calculated in advance and has therefore to be checked prior to the application. Penetration Fenetration SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Physical state Colour: grey Smell: Characteristic Odour threshold: Not determined. jutor 'C boling point or initial boling point and boling range not apply		protection
Breathing equipment: In case of brief exposure or low pollution use breathing filter apparatus. In case of intensive or long exposure use breathing apparatus that is independent of circulating air. Hand protection Do not reuse one-way-gloves Hand Protection: Nitril-rubber-latex-gloves. In case of wearing synthetic protective gloves use cotton-gloves as underwear. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Ansell: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duc-Nix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suplication. Penetration time of glove material subtances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Selection of basole pobserved. Sele		
In case of brief exposure or low pollution use breathing filter apparatus. In case of intensive or long- exposure use breathing apparatus that is independent of circulating air. Hand protection Do not reuse one-way-gloves Hand Protection: Nitril-rubber-latex-gloves. In case of wearing synthetic protective gloves use cotton-gloves as underwear. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Anseli: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. SeECTION 9: Physical and chemical properties SECTION 9: Physical and chemical properties General Information Physical state Colour: grey Smell: Colour: grey Smell: Colour: protective grey Smell: Colour: protective point: >1,000 °C Boiling point or initial boiling point and boiling range not apply		
exposure use breathing apparatus that is independent of circulating air. Hand protection Do not reuse one-way-gloves Hand Protection: Nitril-rubber-latex-gloves. In case of wearing synthetic protective gloves use cotton-gloves as underwear. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Ansell: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duc Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. SECTION 9: Physical and chemical properties SECTION 9: Physical and chemical properties Section 9: Physical and chemical properties Section 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Physical state Colour: grey Smell: Characteristic Odour threshold: Not determined. Physical state Colour: Solid material. Colour: Solid material. Colour (Teshold: Not determined. Phy		reathing filter apparatus. In case of intensive or longe
Hand protection Do not reuse one-way-gloves Hand Protection: Nitril-rubber-latex-gloves. In case of wearing synthetic protective gloves use cotton-gloves as underwear. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Anseli: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the application. Penetration time of glove material aulty and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Sys/face protection Tightly sealed safety glasses. Bodig protection:		
Do not reuse one-way-gloves Hand Protection: Nitril-rubber-latex-gloves. In case of wearing synthetic protective gloves use cotton-gloves as underwear. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Ansell: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection : Protective work clothing. SECTION 9: Physical and chemical properties General Information Physical state Colour: grey Smell: Odour threshold: Not determined. Melting point/freezing point: > 1,000 °C Boiling point or initial boiling point and boiling range Not apply		5
Hand Protection: Nitril-rubber-latex-gloves. In case of wearing synthetic protective gloves use cotton-gloves as underwear. The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Anseli: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eyel/ace protection Tightly sealed safety glasses. Body protection : Protective work clothing. SECTION 9: Physical and chemical properties General Information Physical state Colour: grey Smell: Characteristic Odour threshold: Not determined. >1,000 °C Boiling point or initial boiling point and		
The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Amseli: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information Physical state Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point or initial boiling point and boiling range not apply	Hand Protection: Nitril-rubber-latex-gloves.	
preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Anseli: Flexitrii L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information Physical state Colour: grey Smell: Characteristic Odour threshold: Not determined. Aldour and Solid material. Colour:		
Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Ansell: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uve Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. Section 9: Physical and chemical properties Golur: grey Smell: Characteristic Odour threshold:	0	I resistant to the product/ the substance/ the
preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Anseli: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information Physical state Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: >1,000 °C Boiling point or initial boiling point and boiling range not apply		a deve material can be given for the product/the
Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Ansell: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. Section on basic physical and chemical properties General Information Physical state Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. </td <td></td> <td>e giove material can be given for the product/ the</td>		e giove material can be given for the product/ the
degradation Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Anseli: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties Glour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: >1,000 °C		n of the penetration times rates of diffusion and the
Material of gloves Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Ansel: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Physical state Solid material. Colour: grey Smell: Moti threshold: Not determined. Meting point/freezing point: >1,000 °C Boiling point or initial boiling point and boiling range not apply		
Suitable protective gloves have been determined for activities with products containing cement (GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Ansell: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection : Protective work clothing. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties 9.1 Information Physical state Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: >1,000 °C Boiling point or initial boiling point and boiling range Not apply		
(GISCODES ZP1). Suitable are e.g: Ampri: SolidSafety Cut 081101 / SolidSafety Tough 081201 / SolidSafetyTough Dots 081202 Ansell: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Physical state Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: >1,000 °C Boiling point or initial boiling point and boiling range not apply	0	ed for activities with products containing cement
Ansell: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Physical state Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: >1,000 °C Boiling point or initial boiling point and boiling range not apply		
Ansell: Flexitril L27 / Fleximax 27 or 35 / Hylite / Nitrotough N210 / Sol-Knit KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Physical state Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: >1,000 °C Boiling point or initial boiling point and boiling range not apply		
KCL: Sahara / Gobi / Nitex MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Physical state Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Metting point/freezing point: >1,000 °C Boiling point or initial boiling point and boiling range not apply		
MAPA: Duo-Mix 405 / Enduro 328 / Stansolv AK 22 / Titanlite 397 / Titansuperlite UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Physical state Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: >1,000 °C Boiling point or initial boiling point and boiling range not apply		/ Mitolough M2 10 / 301-Mill
UVEX: uvex Profi Ergo XG 20 / uvex phynomic pro The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information Physical state Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: >1,000 °C Boiling point or initial boiling point and boiling range not apply		K 22 / Titanlite 397 / Titansuperlite
The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information Physical state Colour: grey Smell: Odour threshold: Melting point/freezing point: Plant on initial boiling point and boiling range Not depresed Not apply		
of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties General Information Physical state Colour: grey Smell: Colour: Smell: Colour threshold: Melting point/freezing point: > >1,000 °C Boiling point or initial boiling point and boiling range Not apply		
to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties 9.1 Information on basic physical and chemical properties 9.1 Information Physical state Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: Not determined. Melting point/freezing point: Not apply		
Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties Section on basic physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Physical state Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: >1,000 °C Boiling range not apply		al can not be calculated in advance and has therefore
The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Physical state Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: >1,000 °C Boiling range not apply		
has to be observed. Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Physical state Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: >1,000 °C Boiling point or initial boiling point and boiling range not apply		at has the second state of the
Eye/face protection Tightly sealed safety glasses. Body protection: Protective work clothing. SECTION 9: Physical and chemical properties Secrion on basic physical and chemical properties General Information Physical state Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: >1,000 °C Boiling range not apply		ut by the manufacturer of the protective gloves and
Body protection: Protective work clothing. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Physical state Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: >1,000 °C Boiling range not apply		
SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: >1,000 °C Boiling point or initial boiling point and not apply		00C0.
9.1 Information on basic physical and chemical properties General Information Physical state Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: >1,000 °C Boiling point or initial boiling point and not apply	body protection. I rotective work clothing.	
9.1 Information on basic physical and chemical properties General Information Physical state Solid material. Colour: grey Smell: Characteristic Odour threshold: Not determined. Melting point/freezing point: >1,000 °C Boiling point or initial boiling point and not apply	SECTION 9: Physical and chemical properti	es
General InformationSolid material.Physical stateSolid material.Colour:greySmell:CharacteristicOdour threshold:Not determined.Melting point/freezing point:>1,000 °CBoiling point or initial boiling point and boiling rangenot apply		
Physical stateSolid material.Colour:greySmell:CharacteristicOdour threshold:Not determined.Melting point/freezing point:>1,000 °CBoiling point or initial boiling point andnot apply		
Colour:greySmell:CharacteristicOdour threshold:Not determined.Melting point/freezing point:>1,000 °CBoiling point or initial boiling point and boiling rangenot apply		Solid material
Smell:CharacteristicOdour threshold:Not determined.Melting point/freezing point:>1,000 °CBoiling point or initial boiling point and boiling rangenot apply		
Odour threshold:Not determined.Melting point/freezing point:>1,000 °CBoiling point or initial boiling point and boiling rangenot apply		
Melting point/freezing point:>1,000 °CBoiling point or initial boiling point and>1boiling rangenot apply		
Boiling point or initial boiling point and boiling range not apply		
boiling range not apply		,
		not apply

Printing date 27.09.2023

Version number 1

Revision: 27.09.2023

Trade name: MONOFLEX-S2

		(Contd. of page
Flammability	Not determined.	
Lower and upper explosion limit		
Lower:	Not determined.	
Upper:	Not determined.	
Flash point:	Not applicable	
Decomposition temperature:	Not determined.	
pH at 20 °C	11.4 (1%)	
Viscosity:	11.4 (170)	
Kinematic viscosity	Not applicable.	
dynamic:	Not applicable.	
	Not applicable.	
Solubility		
Water:	miscible	
Partition coefficient n-octanol/water (log		
value)	Not determined.	
Steam pressure:	Not applicable.	
Density and/or relative density		
Density	bulk density	
Relative density	Not determined.	
Vapour density	Not applicable.	
9.2 Other information		
Appearance:		
Form:	Devider	
	Powder	
Important information on protection of heal	tn	
and environment, and on safety.		
Self-inflammability:	Product is not selfigniting.	
Explosive properties:	Product is not explosive.	
Change in condition		
Evaporation rate	Not applicable.	
Information with regard to physical hazard		
classes		
Explosives	Void	
Flammable gases	Void	
Aerosols	Void	
Oxidising gases	Void	
Gases under pressure	Void	
Flammable liquids	Void	
Flammable solids	Void	
Self-reactive substances and mixtures	Void	
Pyrophoric liquids	Void	
	Void	
Pyrophoric solids		
Self-heating substances and mixtures	Void	
Substances and mixtures, which emit		
TIAMMANIA AREAS IN CONTACT WITH WATAR	Void	
flammable gases in contact with water	N / · · ·	
Oxidising liquids	Void	
Oxidising liquids Oxidising solids	Void	
Oxidising liquids Oxidising solids Organic peroxides	Void Void	
Oxidising liquids Oxidising solids Organic peroxides Corrosive to metals Desensitised explosives	Void	

SECTION 10: Stability and reactivity

· 10.1 Reactivity No further relevant information available.

10.2 Chemical stability

• Thermal decomposition / conditions to be avoided: No decomposition if used according to specifications.

(Contd. on page 6)

⁻ GB

Printing date 27.09.2023

Version number 1

Revision: 27.09.2023

Trade name: MONOFLEX-S2

- 10.3 Possibility of hazardous reactions No dangerous reactions known
- · 10.4 Conditions to avoid No further relevant information available.
- 10.5 Incompatible materials: No further relevant information available.
- · 10.6 Hazardous decomposition products: No dangerous decomposition products known

SECTION 11: Toxicological information

- 11.1 Information on hazard classes as defined in Regulation (EC) No 1272/2008
- Acute toxicity Based on available data, the classification criteria are not met.
- · LD/LC50 values that are relevant for classification:

1317-65-3 Calciumcarbonat

- Oral LD50 >5,000 mg/kg (rats)
- Skin corrosion/irritation Causes skin irritation.
- · Serious eye damage/irritation Causes serious eye damage.
- · Respiratory or skin sensitisation May cause an allergic skin reaction.
- 11.2 Information on other hazards
- · Endocrine disrupting properties

None of the ingredients is listed.

SECTION 12: Ecological information

· 12.1 Toxicity

Aquatic toxicity:

1317-65-3 Calciumcarbonat

LC50/96h >10,000 mg/l (rainbow trout)

EC50 (48h) >1,000 mg/l (Daphnia magna)

EC50 289 mg/l /72h (Desmodesmus subspicatus)

- NOEC 75 mg/l /72h (Desmodesmus subspicatus)
- · 12.2 Persistence and degradability No further relevant information available.
- **12.3 Bioaccumulative potential** No further relevant information available.
- 12.4 Mobility in soil No further relevant information available.
- 12.5 Results of PBT and vPvB assessment
- **PBT:** Not applicable.
- **vPvB:** Not applicable.
- · 12.6 Endocrine disrupting properties

The product does not contain substances with endocrine disrupting properties.

- 12.7 Other adverse effects
 Additional ecological information:
- · General notes:

Water hazard class 1 (Self-assessment): slightly hazardous for water.

Do not allow undiluted product or large quantities of it to reach ground water, water bodies or sewage system.

Rinse off of bigger amounts into drains or the aquatic environment may lead to increased pH-values. A high pH-value harms aquatic organisms. In the dilution of the use-level the pH-value is considerably reduced, so that after the use of the product the aqueous waste, emptied into drains, is only low water-dangerous.

SECTION 13: Disposal considerations

13.1 Waste treatment methods

· Recommendation

Must not be disposed of together with household garbage. Do not allow product to reach sewage system.

(Contd. on page 7)

(Contd. of page 5)

Printing date 27.09.2023

Version number 1

Revision: 27.09.2023

(Contd. of page 6)

Trade name: MONOFLEX-S2

- · Uncleaned packagings:
- Recommendation: Disposal must be made according to official regulations.
- Recommended cleaning agent: Water, if necessary with cleaning agent.

SECTION 14: Transport information	
14.1 UN number or ID number ADR, IMDG, IATA	Void
14.2 UN proper shipping name ADR, IMDG, IATA	Void
14.3 Transport hazard class(es)	
ADR, ADN, IMDG, IATA Class	Void
14.4 Packing group ADR, IMDG, IATA	Void
14.5 Environmental hazards:	Not applicable.
14.6 Special precautions for user	Not applicable.
14.7 Maritime transport in bulk accord IMO instruments	ing to Not applicable.
UN "Model Regulation":	Void

SECTION 15: Regulatory information

- 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture
- Directive 2012/18/EU
- · Named dangerous substances ANNEX I None of the ingredients is listed.
- · 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

SECTION 16: Other information

These data are based on our present knowledge. However, they shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

· Relevant phrases

H315 Causes skin irritation.

H317 May cause an allergic skin reaction.

H318 Causes serious eye damage.

H335 May cause respiratory irritation.

- **Department issuing data specification sheet:** Department EHS (Environment-Health-Safety) Environment protection department.
- · Contact: Department EHS (Environment-Health-Safety)

 Abbreviations and acronyms:
 ADR: Accord relatif au transport international des marchandises dangereuses par route (European Agreement Concerning the International Carriage of Dangerous Goods by Road)
 IMDG: International Maritime Code for Dangerous Goods
 IATA: International Air Transport Association
 GHS: Globally Harmonised System of Classification and Labelling of Chemicals
 EINECS: European Inventory of Existing Commercial Chemical Substances
 ELINCS: European List of Notified Chemical Substances
 CAS: Chemical Abstracts Service (division of the American Chemical Society)
 LC50: Lethal concentration, 50 percent

(Contd. on page 8)

⁻ GB

Printing date 27.09.2023

Version number 1

Revision: 27.09.2023

Trade name: MONOFLEX-S2

LD50: Lethal dose, 50 percent PBT: Persistent, Bioaccumulative and Toxic vPvB: very Persistent and very Bioaccumulative Skin Irrit. 2: Skin corrosion/irritation – Category 2 Eye Dam. 1: Serious eye damage/eye irritation – Category 1 Skin Sens. 1: Skin sensitisation – Category 1 STOT SE 3: Specific target organ toxicity (single exposure) – Category 3 (Contd. of page 7)

GB —