

Floor levelling compound with safety fibres

SOLOPLAN®-30 PLUS

Relax in safety for
maximum performance.

The new floor levelling underlayment with safety fibres
guarantees the best outcome and the greatest installation
reliability - while impresses with outstanding levelling properties.

Problems Solved.



schomburg.com

 **SCHOMBURG**

Floor leveling underlayment
with safety fibres

SOLOPLAN®-30-PLUS

**Cement-based self levelling, fibre reinforced
floor levelling underlayment for thicknesses
from 2 to 30 mm.**

Optimized formula, simple to use and outstanding ability
to level, for the best outcome and the greatest installation
reliability.



Technical Data

| | |
|-------|--|
| Basis | Special cement Additives Aggregate |
|-------|--|

| | |
|-----------------------------------|---------------|
| Application/Substrate temperature | +5°C to +25°C |
|-----------------------------------|---------------|

| | |
|-----------|--------------------|
| Pot life* | Approx. 35 minutes |
|-----------|--------------------|

| | |
|---------------|-----------------------|
| Foot traffic* | After approx. 2 hours |
|---------------|-----------------------|

| | |
|---------------------------|------------------------|
| Ready for floor finishes* | After approx. 10 hours |
|---------------------------|------------------------|

| | |
|-------------|---------------------------|
| Application | Hand/Mechanical equipment |
|-------------|---------------------------|

| | |
|-----------|---------------------|
| Packaging | 25 kg polythene bag |
|-----------|---------------------|

* at +23°C and 50% relative humidity

Material demand

| | |
|--------------|--------------------------------|
| Bulk density | Approx. 1.4 kg/dm ³ |
|--------------|--------------------------------|

| | |
|-------------|--|
| Consumption | Approx. 1.65 kg/m ² /mm thickness |
|-------------|--|




Areas of application

- SOLOPLAN-30-PLUS is used at thicknesses from 2 to 30 mm for smoothing, patching and levelling.
- Suitable substrates are concrete, cement-based screeds, old, well bonded tiled finishes and rapid setting cement-based screeds.
- Suitable for exterior and wet duty areas if covered with a suitable SCHOMBURG bonded waterproof membrane.
- Suitable for use in interior rooms in accordance with the French VOC regulation.

Properties

- Fibre reinforced
- Polymer modified
- Self levelling
- Very low emissions
- For interior and exterior use
- Easy to apply
- Rapid setting
- Suitable for heated screeds
- Pumpable
- For thicknesses from 2 to 30 mm in one application



Relax whilst working –
safe results.

Low stress levelling compounds
minimize your risks.

The floor can always look different, the applicator may change –but with new SOLOPLAN-30-PLUS, the quality of work stays at the same high level.

The new floor levelling underlayment with safety fibres guarantees the best outcome and the greatest installation reliability.



High security
fibre technology!



Best levelling,
highly flowable!



Flexible application
by hand or mechanical equipment!

SCHOMBURG GmbH & Co. KG
Aquafinstrasse 2 - 8
D-32760 Detmold (Germany)
phone +49-5231-953-00
fax +49-5231-953-108
email export@schomburg.de
www.schomburg.com



 **SCHOMBURG**