

# ASO<sup>®</sup>-Dichtband-2000-S-Ecke

Corner seal for high loads



Material number	Angle / installation position	Width, article	Material strength	Contents	Packaging	Colour
205933001	90° inside	14 cm	approx. 0.5 mm	1 piece	piece	White with SCHOMBURG logo
205933002	90° outside	14 cm	approx. 0.5 mm	1 piece	piece	White with SCHOMBURG logo

## Product features

- Tear-resistant
- Particularly stretchy
- watertight
- UV-stabilised
- Highly resistant to aggressive media
- Very low emission

## Advantages

- Thin-layer
- Guarantees the drying out of waterproofing materials and thin-bed mortar
- Reliability through prefabrication

## Areas of application

- For the forming of watertight corners
- System component made from ASO<sup>®</sup>-Joint-Tape-2000-S
- System component made from ASO<sup>®</sup>-Joint-Tape-2000

## Areas of application

- For the forming of watertight corners
- System component made from ASO-Joint-Tape-2000-S
- System component made from ASO-Joint-Tape-2000

# ASO<sup>®</sup>-Dichtband-2000-S-Ecke

## Technical Data

### Material properties

Product components	Piece goods
Base material	Composite material: Fleece-membrane-fleece
UV-resistance as per DIN EN ISO 4892-3	≥ 500 hours
Vapour diffusion behaviour	Vapour permeable

### Application

Consumption	1 pc per application
-------------	----------------------

## Application technology

### Aids/tools

Flat trowel

### Suitable substrate

- All substrates in accordance with DIN 18157, Part 1 and in accordance with DIN 18534, DIN 18535, DIN 18531, DIN 18533
- All substrates in accordance with ZDB Code of Practice "Bonded waterproofing (AIV)"

## Usage

### Application

1. On both sides of the joint to be bridged or the wall connection, the waterproofing material is applied at least 2 cm wider than the joint sealing tape.
2. Lay ASO<sup>®</sup>-Dichtband-2000-S-Ecke in the fresh layer.
3. Press the ASO<sup>®</sup>-Dichtband-2000-S-Ecke into the waterproofing layer meticulously without voids or wrinkles, using a flat trowel or pressure roller.
4. Joint-tape edges or connections to pre-formed pieces are applied with an overlap of 5 cm to 10 cm.
5. Bond joint-tape edges or connections with the waterproofing material without wrinkles, covering the whole area, and overcoat after.
6. ASO<sup>®</sup>-Dichtband-2000-S-Ecke must be seamlessly integrated into the area waterproofing.

## Storage conditions

### Storage

Cool, dry, protected from sunlight. Min. 24 months in the original container.

## Disposal

Product leftovers can be disposed of in household waste.

**The recognised standards of construction engineering, the relevant guidelines and current regulations must be observed.**

## ASO<sup>®</sup>-Dichtband-2000-S-Ecke

### Annotations

#### Chemical durability

The chemical resistance after 7 days storage at +22° C exists in the following chemicals:	Concentration (%)
Hydrochloric acid	3%
Sulphuric acid	35%
Citric acid	100.0 g/l
Lactic acid	5%
Caustic potash	20%
Sodium hydroxide	0.3 g/l
Seawater	20.0 g/l

The rights of the buyer with regard to the quality of our materials are based on our terms and conditions of sale and delivery. Our technical advice team will be happy to advise you in the case of requirements that exceed the scope of the application described here. In order to be binding, a legally binding written confirmation is required. The product description does not release the user from a duty of care. Lay a test area in the event of uncertainty. This version becomes invalid in the event of a new version being issued.