

# CRISTALLFUGE

Flexible fine joint mortar 1 – 6 mm



| Material number | Contents | Unit of quantity | Packaging | Colour        |
|-----------------|----------|------------------|-----------|---------------|
| 204274001       | 5        | KG               | Sachets   | Bahama beige  |
| 204274002       | 5        | KG               | Sachets   | beige         |
| 204274003       | 5        | KG               | Sachets   | brown         |
| 204274004       | 5        | KG               | Sachets   | caramel       |
| 204274005       | 5        | KG               | Sachets   | graphite      |
| 204274006       | 5        | KG               | Sachets   | Grey          |
| 204274007       | 5        | KG               | Sachets   | jasmine       |
| 204274008       | 5        | KG               | Sachets   | Jura beige    |
| 204274009       | 5        | KG               | Sachets   | Medium grey   |
| 204274010       | 5        | KG               | Sachets   | nut brown     |
| 204274011       | 5        | KG               | Sachets   | pergamon      |
| 204274012       | 5        | KG               | Sachets   | sand grey     |
| 204274013       | 5        | KG               | Sachets   | silver grey   |
| 204274014       | 5        | KG               | Sachets   | titanium grey |
| 204274015       | 5        | KG               | Sachets   | White         |
| 204274016       | 10       | KG               | Sachets   | Grey          |
| 204274017       | 10       | KG               | Sachets   | Medium grey   |
| 204274018       | 10       | KG               | Sachets   | silver grey   |
| 204274019       | 10       | KG               | Sachets   | titanium grey |
| 204274020       | 10       | KG               | Sachets   | White         |

# CRISTALLFUGE

## Product features

- Cementitious joint mortar
- CG2 in accordance with DIN EN 13888
- Joint widths von 1 mm bis 6 mm
- Pot life of ca. 60 minutes
- Foot traffic after ca. 12 hours

## Advantages

- Tested system product
- Convenient wash-off properties
- Fine surface

## Areas of application

- For grouting tiles and boards made of vitrified tiles and earthenware
- for heated and unheated substrates
- For walls and floors
- For interior

## Technical Data

### Material properties

|                              |                                                       |
|------------------------------|-------------------------------------------------------|
| Product components           | 1 component system                                    |
| Base material                | Cementitious aggregates<br>Special cement<br>Additive |
| Bulk density of fresh mortar | approx. 1.9 kg/dm <sup>3</sup>                        |

### Mixing

|                |                      |
|----------------|----------------------|
| Maturing time  | approx. 2 minutes    |
| Water addition | from 1.25 l to 1.5 l |

### Application

|                                  |                    |
|----------------------------------|--------------------|
| Substrate temperature            | from 5 °C to 25 °C |
| Pot life                         | approx. 60 minutes |
| Foot traffic after               | approx. 12 hours   |
| Application temperature          | from 5 °C to 25 °C |
| Hardening time / full resilience | approx. 2 days     |

## Material consumption

Material consumption rate according to the area of application

| Tile format<br>(in cm) | Joint width<br>(in mm) | Joint depth<br>(in mm) | Approx.<br>consumption /m <sup>2</sup><br>(in kg) |
|------------------------|------------------------|------------------------|---------------------------------------------------|
| 2.0 × 2.0              | 1.5                    | 2.0                    | 0.58                                              |
| 10.0 × 10.0            | 3.0                    | 6.0                    | 0.70                                              |
| 15.0 × 15.0            | 3.0                    | 6.0                    | 0.49                                              |
| 20.0 × 20.0            | 3.0                    | 8.0                    | 0.49                                              |
| 20.0 × 25.0            | 3.0                    | 8.0                    | 0.45                                              |
| 30.0 × 30.0            | 5.0                    | 8.0                    | 0.55                                              |
| 30.0 × 40.0            | 4.0                    | 10.0                   | 0.48                                              |
| 30.0 × 60.0            | 4.0                    | 10.0                   | 0.41                                              |

## CRISTALLFUGE

### Application technology

#### Aids/tools

- Jointing board
- Stirrer
- Clean mixing bucket
- Sponge board

### Suitable covering

Mosaic

### Substrate preparation

#### Requirement for substrate

1. Dry
2. Clean
3. Free of adhesion inhibiting substances

#### Preparing the details

1. After the bedding mortar sets, scratch out the joints sufficiently deep.
2. Next, clean the tiled finish damp.
3. The bedding mortar must be fully set, as otherwise, joint discolourations may occur.
4. Pre-moisten strongly absorbing coverings with water equally.
5. Joint edges must be clean and free of separating substances.
6. The time of tile grouting depends on the thin-bed mortar used.
7. Do not grout on surfaces with different surface temperatures (e.g. due to sun exposure).

### Usage

#### Mixing

1. The consistency of joint mortar must be specified depending on the absorbency of the laying material and substrate.
2. The mix ratio must be kept the same in order to avoid colour differences.
3. Put the water into a clean mixing bucket and mix with the powder component with a stirrer to produce a homogeneous, lump-free mass.
4. After a settling period of ca. 2 minutes, thoroughly homogenise the compound again.

#### Application

1. CRISTALLFUGE is added to the wall and floor areas with a suitable jointing board by exerting slight pressure.
2. Strike off diagonally to the joint cleanly so that the joint cross-section is filled totally.
3. After the joint mortar has sat (check using a finger test), wash the joint contours clean with a moist sponge board.
4. Wash off again with the sponge board after a few minutes.
5. Keep movement joints for elastic grouting with ESCOSIL-2000 free.
6. Scrape out mortar residues after the mortar has sat and wash away with a slightly damp cloth.
7. Wash any mortar film remaining off with the sponge board and clean water after a few hours.
8. The fresh grouting must be protected from influences that damage drying, such as high temperatures, wind, rain, or frost.
9. If weather conditions are poor (low humidity, draughts, wind) and the ceramic shards are highly absorbent, the joint cross-section must be cured with clean water (re-wet with the sponge board).
10. Replace the water arising from washing off on a regular basis.
11. We recommend performing trial jointing (pre-wet the surface if necessary or impregnate with suitable materials prior to grouting) on coatings with profiled, rough, unglazed or porous surfaces.
12. The washing time depends on the coating material and the prevailing climate.
13. After sufficient standing time, smooth the surface slightly without washing the joint out.
14. In order to perform a complete filling in one application step, only remove the excess joint mortar after a short standing time (30-60 sec.).

#### Cleaning tools

Clean tools thoroughly with water after use.

### Storage conditions

#### Storage

Store in a cool and dry place. Min. 12 months in the original canister. Promptly use opened canister.

## CRISTALLFUGE

### Disposal

Product leftovers can be disposed of in accordance with disposal code AVW 17 01 01.

### Notes

- Protect surfaces that are not to be treated from the effects of CRISTALLFUGE!
- Do not add water or new mortar to existing CRISTALLFUGE mortar that has already set in order to make it workable again. (Risk of inadequate strength development)
- We recommend using neutral or slightly alkaline cleaning materials in the prescribed application concentrations for regular care and cleaning on the grouted surfaces. Rinse the surface with clean water after cleaning.
- The applicable regulations must be observed if cleaning materials containing acid are used! Pay attention to the product-specific properties of the laying materials! Pre-dampen the joints and then apply the cleaning materials at a low application concentration. The cleaner's action time must be kept to a minimum. Then wash it off with a large amount of clean water. Cleaning materials containing acid impair the joint mortar's strength and can even destroy the grout matrix totally if used improperly, e.g. doses that are too high, excessive action times or no pre-wetting the grout net.
- Only use clean water and clean tools!
- Clean the grouted surfaces including the joint chambers thoroughly before starting grouting.
- Observe the setting times for adhesive and mortar! Premature grouting poses the risk of uneven colours in the grout finish.
- Protect the freshly applied joint mortar from sunlight, high temperatures, draughts, moisture and frost (until it reaches its final strength).
- Close joints between covering fields, assembly parts, pipe penetrations and corner and connecting joints elastically using ESCOSIL-2000-ST or ESCOSIL-2000 depending on the application!
- Uneven moisture penetration due to the sub-base, mortar bed, temperature differences or coating material can cause colour variations in the grout finish. These do not affect the joint mortar's quality and can be rectified increasingly by favourable ambient conditions. For this reason, the coloured appearance of the joint same rods may differ from the actual joint colour. No guarantee for differences in colour!
- If there are higher mechanical loads, e.g. due to cleaning devices or chem. exposure, we recommend using the ASODUR®-EKF or CRISTALLFUGE-EPOX heavy-duty, 2 component epoxy resin joint as the joint material if the production-specific properties of the natural stone material allow this!
- When grouting natural and synthetic stone tiles, take into account the specific properties (tendency to discolour). Perform trial jointing if in doubt!


### Observe applicable safety data sheet!

GISCODE: ZP1

## CRISTALLFUGE

### Annotations

#### Colours

|                                                                                     |               |
|-------------------------------------------------------------------------------------|---------------|
|    | White         |
|    | titanium grey |
|    | silver grey   |
|    | sand grey     |
|    | pergamon      |
|    | nut brown     |
|    | Medium grey   |
|    | Jura beige    |
|  | jasmine       |
|  | Grey          |
|  | graphite      |
|  | caramel       |
|  | brown         |
|  | beige         |
|  | Bahama beige  |

The rights of the buyer with regard to the quality of our materials are based on our terms and conditions of sale and delivery. Our technical advice team will be happy to advise you in the case of requirements that exceed the scope of the application described here. In order to be binding, a legally binding written confirmation is required. The product description does not release the user from a duty of care. Lay a test area in the event of uncertainty. This version becomes invalid in the event of a new version being issued.