

Floor levelling compound



SOLOPLAN®

The floor levelling compound for interior use with highly convenient application.

Problems Solved.



 **SCHOMBURG**

Floor levelling compound for interior use

SOLOPLAN®

Self-levelling, cement-based floor levelling compound
for layer thicknesses from 2 to 20 mm.

Modern recipe of floor levelling compound with high
flowability and also ready to receive ceramic tiles earlier.



Technical data

Basis Cement, aggregate, additives

Application /
substrate temperature +5 °C to +25 °C

Pot life* 30 minutes


Foot traffic after* after approx. 3 hours

Packaging 25 kg foil bag

* at +23 °C and 50% rel. humidity

Material consumption

Consumption ca. 1.7 kg/m²/mm
layer thickness



Application areas

- SOLOPLAN is used in a layer thickness of 2-20 mm for smoothing, filling, repairing and levelling.
- Suitable substrates include floor surfaces made of concrete in accordance with DIN 1045, heated and unheated cement-based screeds in accordance with DIN 18560, old, firmly adhered tiled finishes.
- SOLOPLAN is suitable for areas exposed to water, if a suitable SCHOMBURG bonded waterproof system is applied subsequently (up to W1-I).
- SOLOPLAN is suitable for interior use, in accordance with the French VOC ordinance. Very low emissions in accordance with GEV-EMICODE, can be used for DGNB, LEED, BREEAM, HQE. Highest quality stage 4, line 8.

Properties

- For layer thicknesses from 2-20 mm in one application step.
- Already ready for ceramic laying after 4 hours.
- For interior.
- Self-levelling.
- Polymer modified.
- Very low emission.
- Easy to process.
- Suitable for heated screeds.
- Pumpable.



Successful working –
Dependable results.
The earlier workability
increases your efficiency.

Floors can vary greatly and workers can change – stay independent and flexible with the new SOLOPLAN. The new floor levelling compound with convenient application and also ready for covering earlier.



**Best
levelling**
High flowability



**Smooth
application**
Very convenient



**Rapid construction
progress**
Easy application

SCHOMBURG GmbH & Co. KG
Aquafinstraße 2-8
D-32760 Detmold (Germany)
phone +49-5231-953-00
fax +49-5231-953-108
email export@schomburg.de
www.schomburg.com



 **SCHOMBURG**