

SCHOMBURG GmbH & Co. KG  
Aquafinstraße 2-8  
D-32760 Detmold (Germany)  
phone +49-5231-953-00  
fax +49-5231-953-108  
email export@schomburg.de  
www.schomburg.com



 **SCHOMBURG**

## Technical Data Sheet

# INDU-FibreFiller

## Thixotropic material

**Art.-No. 2 03501**

### Properties:

INDU-FibreFiller can be used to thicken and improve the thixotropy of all solvent free INDUFLOOR coatings. The addition of INDU-FibreFiller controls the slip and flow properties so that non-slip smoothing mortars for vertical or strongly sloping surfaces can be produced on site.

### Technical Data:

Packaging: 2 kg bag and 10 kg sack  
Storage: 36 months when stored cool and dry above +10° C in the original unopened packaging.

### Application:

INDU-FibreFiller is supplied in a ready to use powder form.  
INDU-FibreFiller can be mixed into the coating material (best into the resin component) with a suitable rotating mixer with paddle (rapid stirrer).  
Ensure an even lump free preparation. The addition rate lies between 0.5 up to a maximum of 5% by weight and is dependent on the thickness to be applied and the degree of fall on the substrate to be coated.

Please observe a valid EU Health & Safety Data Sheet.